

PHYSICAL PROPERTIES

Monofilament Diameter _____ 010
ASTM D-204

Flammability Rating _____ UL

Recommended Cutting _____ Shears

Colors _____ 1

Wall Thickness _____ .025

Abrasion _____ Low

Melt Point
ASTM D-2117
449°F (232°C)

Maximum Continuous
Mil-I-23053
302°F (150°C)

Minimum Continuous
-40°F (40°C)



CHEMICAL RESISTANCE

1=No Effect 4=More Affected
2=Little Effect 5=Severely Affected
3=Affected

Aromatic Solvents _____ 2

Aliphatic Solvents _____ 1

Chlorinated Solvents _____ 3

Weak Bases _____ 1

Salts _____ 1

Strong Bases _____ 2

Salt Water 0-S-1926 _____ 1

Hydraulic Fluid MIL-H-5606 _____ 1

Lube Oil MIL-L-7808 _____ 1

De-Icing Fluid MIL-A-8243 _____ 1

Strong Acids _____ 3

Strong Oxidants _____ 2

Esters/Ketones _____ 1

UV Light _____ 1

Petroleum _____ 1


Fungus ASTM G-21 _____ 1

RoHS _____ Yes



FLAMMABILITY

Rating _____ UL, VW-1



TECHFLEX

Braided Sleeving Products

www.techflex.com

800.323.5140 • 973.300.9242 • fax: 973.300.9409
104 Demarest Road • Sparta, NJ 07871

VW-1

