



Melt Point
ASTM D-2117
449°F (232°C)



www.techflex.com

CHEMICAL RESISTANCE

- 1=No Effect
- 2=Little Effect
- 3=Affected
- 4=More Affected
- 5=Severely Affected

Aromatic Solvents _____	1
Aliphatic Solvents _____	1
Chlorinated Solvents _____	1
Weak Bases _____	1
Salts _____	1
Strong Bases _____	2
Salt Water 0-S-1926 _____	1
Hydraulic Fluid MIL-H-5606 _____	1
Lube Oil MIL-L-7808 _____	1
De-Icing Fluid MIL-A-8243 _____	1
Strong Acids _____	5
Strong Oxidants _____	5
Esters/Ketones _____	1
UV Light _____	2
Petroleum _____	2
Fungus ASTM G-21 _____	2
Halogen Free _____	Yes
RoHS _____	Yes

PHYSICAL PROPERTIES

Monofilament Diameter _____	.005-.010
ASTM D-204	
Flammability Rating _____	Non Flammable
Recommended Cutting _____	Shears
Colors _____	1
Wall Thickness _____	.013-.025
Specific Gravity ASTM D-792 _____	8.9
Moisture Absorption _____	NA
% ASTM D-570	

FLAMMABILITY

Rating _____ Non Flammable



www.techflex.com
800.323.5140 • 973.300.9242 • fax: 973.300.9409
104 Demarest Road • Sparta, NJ 07871

